

**Determination of installed thermal resistance into a roof and into a wall of
MIX FIBRE DE BOIS according to EN ISO 6946:2017**

(test name)

Test method: Determination of installed thermal resistance into a roof and into a wall of MIX FIBRE DE BOIS 80 according to EN ISO 6946:2017

(number of normative document or test method, description of test procedure, test uncertainty)

Product name: MIX FIBRE DE BOIS 80

(identification of the specimen)

Customer: SAS ATI FRANCE, 146 Avenue du Bicentenaire – FR-01120 Dagneux, France

(name and address of enterprise)

Manufacturer: SAS ATI FRANCE, 146 Avenue du Bicentenaire – FR-01120 Dagneux, France

Calculation results:

Roof slope angle, α	Calculation method reference no.	Calculation result, R , (m ² ·K)/W
Pitched roof ($\alpha = 0^\circ$)	EN ISO 6946:2017	6.09
Pitched roof ($\alpha = 30^\circ$)		6.17
Pitched roof ($\alpha = 45^\circ$)		6.21
Wall ($\alpha = 90^\circ$)		6.39

R value for others pitched sloop (different α value) can be determined by linear interpolation between two calculated R values

Calculation made by: Building Physics Laboratory, Institute of Architecture and Construction of Kaunas University of Technology

(Name of the organization)

Products used in calculation: Multilayer reflective insulation product PRO W (110 mm) (test report no. 129 SF/22 U)

Declared thickness of product PRO W – 80±10 mm

Panel of biosourced insulation with vegetal fibers PAVAFLEX CONFORT (80 mm) (manufacturer SOPREMA SAS certificate: No.17/006/1259)

Additional information: Application, 2022-06-09

Annex: Annex 1. Calculation results

(the numbers of the annexes should be pointed out)

Head of Laboratory: _____

(approves the test results)


K. Banionis

(n., surname)


(signature)

Calculated by _____

(calculation made by)



A. Stonkuvienė

(n., surname)



(signature)

Validity – the named data and results refer exclusively to the tested and described specimens.
Notes on publication – no part of this document may be photocopied, reproduced or translated to another language without the prior written consent of the Building Physics Laboratory.

Annex 1: Calculation results

Table 1: Products R- values

Product	Thermal resistance R, (m ² ·K)/W
PRO W (test report No. 129 SF/22 U)	R_{core90/90} = 3.25
PAVAFLEX CONFORT 80 (manufacturer SOPREMA SAS certificate: No.17/006/1259)	R = 2.10
<p><i>"R_{core90/90}" is the declared R core value following EN 16012 + A1.</i> <i>"R_{core90/90}" is calculated on 4 results of 4 samples came from 4 different fabrication dates following EN 16012 + A1 (and using the fractile 90/90 calculation rules $S_{R-prod} = \sqrt{\frac{\sum(R_i - R_{average})^2}{n-1}}$);</i></p>	



Temperature regime 20°C / 0°C	
1.	Unventilated Air cavity #1, 20 mm
2.	PAVAFLEX CONFORT 80, 80 mm
3.	Unventilated Air cavity #2, 20 mm
4.	PRO W, 110 mm
5.	Ventilated Air cavity #3, 20 mm

Figure 1. Roof construction design

Table 2: Roof construction calculation results for slope $\alpha = 0^\circ$ (EN ISO 6946)

MIX FIBRE DE BOIS 80 installed on roof			
Angle: $\alpha = 0^\circ$	Layer	R value	Unit
Ascendant Heat Flux (Winter period)	Unventilated Air cavity # 1	0.1515	m ² ·K/W
	PAVAFLEX CONFORT 80	2.10	m ² ·K/W
	Unventilated Air cavity # 2	0.4421	m ² ·K/W
	PRO W	3.25	m ² ·K/W
	Ventilated Air cavity # 3	0.1475	m ² ·K/W
	R Total	6.09	m²·K/W

Validity – the named data and results refer exclusively to the tested and described specimens.
 Notes on publication – no part of this document may be photocopied, reproduced or translated to another language without the prior written consent of the Building Physics Laboratory.

Table 3: Roof construction calculation results for slope $\alpha = 30^\circ$ (EN ISO 6946)

MIX FIBRE DE BOIS 80 installed on roof			
Angle: $\alpha = 30^\circ$	Layer	R value	Unit
Ascendant Heat Flux (Winter period)	Unventilated Air cavity # 1	0.1571	m ² ·K/W
	PAVAFLEX CONFORT 80	2.10	m ² ·K/W
	Unventilated Air cavity # 2	0.4930	m ² ·K/W
	PRO W	3.25	m ² ·K/W
	Ventilated Air cavity # 3	0.1672	m ² ·K/W
	R Total	6.17	m²·K/W

Table 4: Roof construction calculation results for slope $\alpha = 45^\circ$ (EN ISO 6946)

MIX FIBRE DE BOIS 80 installed on roof			
Angle: $\alpha = 45^\circ$	Layer	R value	Unit
Ascendant Heat Flux (Winter period)	Unventilated Air cavity # 1	0.1600	m ² ·K/W
	PAVAFLEX CONFORT 80	2.10	m ² ·K/W
	Unventilated Air cavity # 2	0.5231	m ² ·K/W
	PRO W	3.25	m ² ·K/W
	Ventilated Air cavity # 3	0.1792	m ² ·K/W
	R Total	6.21	m²·K/W

Table 5: Wall construction calculation results for slope $\alpha = 90^\circ$ (EN ISO 6946)

MIX FIBRE DE BOIS 80 installed on wall			
Angle: $\alpha = 90^\circ$	Layer	R value	Unit
Ascendant Heat Flux (Winter period)	Unventilated Air cavity # 1	0.1695	m ² ·K/W
	PAVAFLEX CONFORT 80	2.10	m ² ·K/W
	Unventilated Air cavity # 2	0.6403	m ² ·K/W
	PRO W	3.25	m ² ·K/W
	Ventilated Air cavity # 3	0.2336	m ² ·K/W
	R Total	6.39	m²·K/W

Requirements for calculation validity:

- Calculations of R values are valid for a pitched roof (α is generally from 30° to 90°).
- Calculations of R values are valid when MIX FIBRE DE BOIS 80 is installed from the internal side of the Roof or the external part of the Roof.
- Calculations of R values are valid when MIX FIBRE DE BOIS 80 is installed in agreement with the installation guidelines described into the manufacturer brochure.

Validity – the named data and results refer exclusively to the tested and described specimens.
Notes on publication – no part of this document may be photocopied, reproduced or translated to another language without the prior written consent of the Building Physics Laboratory.